

CONVEYOR AND PROCESS BELTS

NA-1138

CODE

TECHNICAL DATA SHEET

NT1 HS

14/11/00								
COMPOSITION								
	Material	Synthetic elastomer						
e a	Thickness	0.20 mm <i>0.008 in.</i>						
Conveying surface	Surface pattern	SK						
Con	Colour	Green						
	Coefficient of friction	MF						
e S	Material	Polyamide (PA)						
Textile carcass	Plies no.	3						
F 8	Weft type	Flexible						
	Material	Fabric with polyurethane (TPU) impregnation						
Driving Surface	Thickness	mm in.						
Driv	Surface pattern	Fabric						
	Colour	Black						

Total thickness	1.20 mm	0.05	in.	
Weight	1.20 kg/m ²	0.24	lbs./sq.ft	
Elongation at 1%	3 N/mm	17.0	lbs./in.	
Max. admissible pull	6 N/mm	34.3	lbs./in.	
Temperature resistance (1)	min.	-20 °C	-4	°F
resistance (1)	max.	100 °C	212	°F
(1) use of the belt with limit	values may re	duce its life		
Minimum roller diame	eter ⁽²⁾			
Knife edge	no			
Bending roller	15 mm	0.6	in.	
■ Counter-bending ro	15 mm	0.6	in.	
(2) The above mentioned v	alues depend	on the type of CHIOF	RINO joint i	recommend

Raw steel sheet	0.20 [-]
Laminated plastic/wood	0.25 [-]
Steel roller	0.20 [-]
Rubberized roller	0.30 [-]

TECHNICAL SPECIFICATIONS

Max. production width $1800 \; \text{mm}$ 71 in.


SUITABLE FOR

Wood industry Paper industry: cutters Printing and graphic: stacking

Printing and graphic: insertion cassettes wind./unwinding

Printing and graphic: wrapping / binding

Packaging



FEATURES	
Humidity influence	yes
Suitable to metal detector	no
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	yes
Swan neck conveying	no
Inclined conveying	yes
Accumulators belts	no
Curved conveyor	no
Chemical resistances <u>link</u>	6

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

Issue: 10-10-2011 Last Update: 01-03-2019

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.



CONVEYOR AND PROCESS BELTS

JOINING DATA SHEET

NT1 HS NA-1138 CODE **TYPE**

SKIVED JOINT '4' · Recommended joining procedure



Check our general catalogue to get further info on CHIORINO joining methods.

· Skiving instructions

Skiver	Belt Length			Cam/	Pulley			Top cover				
	thickness		diagonal cut	wedge number	Т	В	Thickness adjustment	working	Т	В	Thickness adjustment	End stop switch of working
	mm	mm			mm	mm		plate	mm	mm		plate
B600 A	1,3	25	Straight	2-10	19	0	17.5		19	0	17.5	
B300 SA	1,3	25	Straight	2-10	24	0	11-03		24	0	11-01	

· Guide to the use of adhesives

Apply the K cement on the polyamide part of the splices.


Let dry for 5 minutes, then match the belt ends, paying attention to align properly.

Press according to the instructions shown.

To ensure best joint life it is advisable not to run or tension the belt for 24 hours.

Kit: NAILCOL

· Layout of components



Press settings						
Upper platen temperature	100 °C					
Lower platen temperature	100 °C					
Curing time in press	5 min.					
Driving torque	30					

Cooling time: it is recommended to remove the belt from the press once a temperature of 60/70 degrees C is reached.

Notes

Issue: 16-12-2011 Last Update: 04-12-2014

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.